

KRK KUMAGAI RIKI KOGYO

Ink Drying Tester

Model No. 2302

Drying property of letterpress or lithography ink is evaluated, by measuring the time till the ink dries and it is not transferred to the paper even if it is pressed against the paper. Gravure ink or other inks that are dried by heating or another process cannot be used on this tester. Test principle: a printing specimen and a counter-paper-sheet are overlapped and wound around the drum rotating at a constant speed; upon them, a press gear that applies a constant load is put, and it is moved along with rotation of the drum. From the trace of the press gear on the counter-paper-sheet, the drying time and set-off of the specimen are measured.

Drum	103mm in outer diameter, 300mm long, made of acrylic resin
Rotation Speed	1/10rpm, total scanning time 15 hours 1rpm, total scanning time 1.5 hours
Press Gear	geometry specified by JIS, press pressure 750+20gf (7.36+0.20N)
Referential Standard	JIS k-5701-2000
Power Source	100/110VAC 50/60Hz 2A
Outer Dimensions	660×210×265mm
Instrument Weight	16kg



Sold & serviced by:

OpTest Equipment Inc.

www.optest.com - sales@optest.com - +1-613-632-5169